

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
26 April 2001 (26.04.2001)

PCT

(10) International Publication Number  
**WO 01/28492 A2**

(51) International Patent Classification<sup>7</sup>: A61K

(21) International Application Number: PCT/US00/27962

(22) International Filing Date: 11 October 2000 (11.10.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/422,294 21 October 1999 (21.10.1999) US

(71) Applicant: RUTGERS, THE STATE UNIVERSITY  
[US/US]; Old Queens Building, Somerset and George  
Streets, New Brunswick, NJ 08901 (US).

(72) Inventor: UHRICH, Kathryn, E.; 920 Bloomfield Street,  
#1, Hoboken, NJ 07030 (US).

(74) Agent: VISKNINS, Ann, S.; Schwegman, Lundberg,  
Woessner & Kluth, P.O. Box 2938, Minneapolis, MN  
55402 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— Without international search report and to be republished upon receipt of that report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



**WO 01/28492 A2**

(54) Title: POLYANHYDRIDES WITH BIOLOGICALLY ACTIVE DEGRADATION PRODUCTS

(57) Abstract: Polyanhydrides which degrade into biologically active salicylates and alpha-hydroxy acids and methods of using these polyanhydrides to deliver the salicylates and alphahydroxy acids to a host are provided.

-1-

**POLYANHYDRIDES WITH BIOLOGICALLY ACTIVE DEGRADATION  
PRODUCTS**

**5 Field of the Invention**

Biocompatible polyanhydrides having improved degradation properties and processability with useful degradation products have now been developed. In one embodiment, the polyanhydrides are ortho-substituted aromatic polyanhydrides produced from ortho-substituted bis-aromatic carboxylic acid anhydrides which degrade into biologically active materials such as salicylates. In another embodiment, the polyanhydrides are aliphatic in structure and degrade into alpha-hydroxy acids.

15 Salicylates are used routinely as anti-inflammatory, antipyretic, analgesic, and anti-oxidant agents, while alpha-hydroxy acids are incorporated into many skin moisturizers, cleansers, lotions, creams shampoos, tanning products and lipsticks to promote smoother, clearer skin with fewer wrinkles. Thus, the biocompatible polyanhydrides of the present invention can be administered to a host via a variety of routes including, but not limited to orally, subcutaneously, intramuscularly, intradermally and topically, depending upon the degradation product of the polyanhydride and the selected use for the degradation product.

**Background of the Invention**

Polymers comprising aromatic or aliphatic anhydrides have been studied extensively over the years for a variety of uses. For example, in the 1930s fibers comprising aliphatic polyanhydrides were prepared for use in the

-2-

textile industry. In the mid 1950s, aromatic polyanhydrides were prepared with improved film and fiber forming properties. More recently, attempts have been made to synthesize polyanhydrides with greater thermal and hydrolytic stability and sustained drug release properties.

U.S. Patents 4,757,128 and 4,997,904 disclose the preparation of polyanhydrides with improved sustained drug release properties from pure, isolated prepolymers of diacids and acetic acid. However, these biocompatible and biodegradable aromatic polyanhydrides have radical or aliphatic bonds resulting in compounds with slow degradation times as well as relatively insoluble degradation products unless incorporated into a copolymer containing a more hydrophilic monomer, such as sebacic acid. The aromatic polyanhydrides disclosed in the '128 Patent and the '904 Patent are also insoluble in most organic solvents. A bioerodible controlled release device produced as a homogenous polymeric matrix from polyanhydrides with aliphatic bonds having weight average molecular weights greater than 20,000 and an intrinsic viscosity greater than 0.3 dL/g and a biologically active substance is also described in U.S. Patent 4,888,176. Another bioerodible matrix material for controlled delivery of bioactive compounds comprising polyanhydride polymers with a uniform distribution of aliphatic and aromatic residues is disclosed in U.S. Patent 4,857,311.

Biocompatible and biodegradable aromatic polyanhydrides prepared from para-substituted bis-aromatic dicarboxylic acids for use in wound closure devices are disclosed in U.S. Patent 5,264,540. However, these compounds exhibit high melt and glass transition temperatures and decreased solubility, thus making them difficult to process. The disclosed polyanhydrides also comprise radical or aliphatic bonds which can not be hydrolyzed by water.


-3-

Polyanhydride polymeric matrices have also been described for use in orthopedic and dental applications. For example, U.S. Patent 4,886,870 discloses a bioerodible article useful for prosthesis and implantation which  
5 comprises a biocompatible, hydrophobic polyanhydride matrix. U.S. Patent 5,902,599 also discloses biodegradable polymer networks for use in a variety of dental and orthopedic applications which are formed by polymerizing anhydride prepolymers.

10 Biocompatible and biodegradable polyanhydrides have now been developed with improved degradation, processing and solubility properties, as well as utilities based upon their degradation products.

#### Summary of the Invention

15 An object of the present invention is to provide biocompatible and biodegradable polyanhydrides which degrade into biologically active products. In one embodiment, aromatic polyanhydrides which degrade into biologically active salicylates are prepared from ortho-  
20 substituted bis-aromatic carboxylic acid anhydrides. Ortho substitution disrupts the crystallinity of the resulting polymer, enhancing solubility and processability, as well as degradation properties. The use of hydrolyzable bonds such as esters, amides, urethanes, carbamates and  
25 carbonates as opposed to radical or aliphatic bonds in these compounds further enhances these properties. In this embodiment, the polyanhydride comprises a repeating unit within the structure of Formula I:




wherein Ar is a substituted or unsubstituted aromatic ring and R is a difunctional organic moiety substituted on each  
35 Ar ortho to the anhydride group. Ar and R are preferably

-4-

selected so that the hydrolysis products of the polyanhydrides have a chemical structure resembling biologically active materials, particularly salicylates such as aspirin, nonsteroidal anti-inflammatory naphthyl or phenyl propionates such as ibuprofen, ketoprofen, naproxen, and the like, or other aromatic anti-inflammatory compounds such as indomethacin, indoprofen, and the like. Ar is preferably a phenyl group and R is preferably  $-Z_1-R_1-Z_1-$  in which  $R_1$  is a difunctional moiety and both  $Z_1$ s are independently either an ester, amide, anhydride, carbonate, urethane or sulfide groups.  $R_1$  is preferably an alkylene group containing from 1 to 20 carbon atoms, or a group with 2-20 carbon atoms having a structure selected from  $(-CH_2-CH_2-O-)_m$ ,  $(CH_2-CH_2-CH_2-O-)_m$  and  $(-CH_2-CH(CH_3)-O-)_m$ .

Ortho-substituted bis-aromatic carboxylic acid anhydrides are used in the preparation of the aromatic polyanhydrides of the present invention. The ortho-substituted bis-aromatic carboxylic acid anhydrides have the structure of Formula II:




wherein Ar and R, and the preferred species thereof, are the same as described above with respect to Formula I and R is substituted on each Ar ortho to the anhydride group.

In another embodiment, polyanhydrides which degrade into biologically active alpha-hydroxy acids are prepared from bis-carboxylic acid anhydrides. In this embodiment, the polyanhydride comprises a repeating unit within the structure of Formula III:



-5-

wherein, R is preferably selected so that the hydrolysis products of the polyanhydrides have a chemical structure resembling an alpha-hydroxy acid. In this embodiment, R is preferably an alkylene group containing from 1 to 20 carbon atoms,  $-(CH_2)_x-$  wherein x is from 1 to 20, or



10


that the R group contains from 1 to 40 hydroxyl groups.

The present invention relates to compositions and methods of using compositions comprising polyanhydrides of Formula (I) or (III) in applications wherein delivery of a salicylate or an alpha-hydroxy acid to a host is desired. By "host" it is meant to include both animals and plants.

A more complete appreciation of the invention and other intended advantages can be readily obtained by reference to the following detailed description of the preferred embodiments and claims, which disclose the principles of the invention and the best modes which are presently contemplated for carrying them out.

#### Detailed Description of the Invention

Polyanhydrides which degrade into useful biologically active products such as salicylates and alpha-hydroxy acids have now been developed. Compounds comprising these polyanhydrides are useful in a variety of applications wherein delivery of a salicylate or alpha-hydroxy acid is desired. In one embodiment, the polyanhydride comprises repeating units with the structure of Formula I:



wherein Ar is a substituted or unsubstituted aromatic ring

-6-

and R is a difunctional organic moiety substituted on each Ar ortho to the anhydride group. In this embodiment, Ar and R are preferably selected so that the hydrolysis products of the polyanhydrides have a chemical structure resembling biologically active materials, particularly salicylates such as aspirin, nonsteroidal anti-inflammatory naphthyl or phenyl propionates such as ibuprofen, ketoprofen, naproxen, and the like, or other aromatic anti-inflammatory compounds such as indomethacin, indoprofen, and the like. Examples of the biologically active salicylates include, but are not limited to, thymotic acid, 4,4-sulfinyldinailine, 4-sulfanilamidosalicylic acid, sulfanilic acid, sulfanilylbenzylamine, sulfaloxic acid, succisulfone, salicylsulfuric acid, salsallate, salicylic alcohol, orthocaine, mesalamine, gentisic acid, enfenamic acid, cresotic acid, aminosalicic acid, aminophenylacetic acid, acetylsalicic acid, and the like. The identification of Ar and R moieties that provide aromatic polyanhydrides that hydrolyze to form such biologically active salicylates can be readily determined by those of ordinary skill in the art without undue experimentation. In particular, Ar is preferably a phenyl group and R is preferably  $-Z_1-R_1-Z_1-$  in which  $R_1$  is a difunctional moiety and both  $Z_1$ s are independently either an ester, amide, anhydride, carbonate, urethane or sulfide groups.  $R_1$  is preferably an alkylene group containing from 1 to 20 carbon atoms, or a group with 2-20 carbon atoms having a structure selected from  $(-CH_2-CH_2-O-)_m$ ,  $(CH_2-CH_2-CH_2-O-)_m$  and  $(-CH_2-CHCH_3-O-)_m$  or  $R_1$  may have the structure  $-R_2-Z_2-R_3-$  wherein  $R_2$  and  $R_3$  are independently alkylene groups containing from 1 to 19 carbon atoms or groups having from 2 to 18 carbon atoms having a structure selected from  $(-CH_2-CH_2-O-)_m$ ,  $(-CH_2-CH_2-CH_2-O-)_m$ , and  $(-CH_2-CHCH_3-O-)_m$ , and  $Z_2$  is selected from the difunctional moieties described above with respect to  $Z_1$ .

-7-


Ar may be an alkylaryl group, in which a difunctional organic moiety is positioned between each anhydride carbonyl group and the corresponding aromatic ring. Preferably, however, each carbonyl group is directly substituted on the corresponding aromatic ring.

Preferred polymers of this embodiment have repeating units with the structure of Formula I in which Ar is a phenyl ring and R is selected from  $-Z_1(-CH_2-)_n-Z_1-$ ,  $-Z_1(-CH_2-CH_2-O-)_m-Z_1-$ ,  $-Z_1(-CH_2-CH_2-CH_2-O-)_m-Z_1-$ , and  $-Z_1(-CH_2-CHCH_3-O-)_m-Z_1-$ , wherein  $Z_1$  is an ester or amide group and n is from 1 to 20 inclusive, and preferably is 6, and m is selected so that R has from 2 to 20, and preferably 6, carbon atoms.

The aromatic polyanhydrides of this embodiment of the present invention may be prepared by the method described in Conix, Macromol. Synth., 2, 95-99 (1996), in which dicarboxylic acids are acetylated in an excess of acetic anhydride at reflux temperatures followed by melt condensation of the resulting carboxylic acid anhydride at 180°C for 2-3 hours. The resulting polymers are isolated by precipitation into diethylether from methylene chloride. The described process is essentially the conventional method for polymerizing bisaromatic dicarboxylic acid anhydrides into aromatic polyanhydrides.

Aromatic polyanhydrides in accordance with this embodiment of the present invention have average molecular weights of at least about 1500 daltons, up to about 100,000 daltons, calculated by Gel Permeation Chromatography (GPC) relative to narrow molecular weight polystyrene standards.

These aromatic polyanhydrides are produced from ortho-substituted bis-aromatic carboxylic acid anhydrides having the structure of Formula II:




35



-8-

in which Ar, R and the preferred species thereof are the same as described above with respect to Formula I. As noted above, ortho-substituted bis-aromatic carboxylic acid anhydrides are prepared by acetylation of the corresponding  
5 ortho-substituted bis-aromatic carboxylic acids in an excess of acetic anhydride at reflux temperatures. The dicarboxylic acids have the structure of Formula IV,




wherein Ar, R and the preferred species thereof are the same as described above with respect to Formula I.

The dicarboxylic acids are prepared by reacting a  
15 stoichiometric ratio of aromatic carboxylic acid having the structure  $\text{Z}_3-\text{Ar}-\text{COOH}$  and a compound having a structure  $\text{Z}_4-\text{R}-\text{Z}_4$ , wherein Ar is a substituted or unsubstituted aromatic ring on which  $\text{Z}_3$  is substituted ortho to the carboxylic acid group, R is a difunctional organic moiety and  $\text{Z}_3$  and  $\text{Z}_4$  are  
20 functional groups selected to provide the linkage desired between the difunctional organic moiety and the two aromatic rings.

Suitable  $\text{Z}_3$  and  $\text{Z}_4$  functional groups, and the manner in which they may be reacted to produce the bis-aromatic  
25 dicarboxylic acids of the present invention, may be readily determined by those of ordinary skill in the art without undue experimentation. For example, for aromatic polyanhydrides having the structure of Formula I in which Ar is a phenyl group and R is  $-\text{O}-(\text{CH}_2)_6-\text{O}-$ , the ortho-  
30 substituted bisaromatic dicarboxylic acid starting material may be prepared by reacting o-salicylic acid with 1,6-dibromohexane.


In another embodiment, the polyanhydrides degrade into biologically active alpha-hydroxy acids and comprise a  
35 repeating unit within the structure of Formula III:

-9-



In this embodiment, R is preferably selected so that the  
 5 hydrolysis products of the polyanhydrides have a chemical  
 structure resembling an alpha-hydroxy acids. In this  
 embodiment, R is preferably an alkylene group containing  
 from 1 to 20 carbon atoms,  $-(\text{CH}_2)_x-$  wherein x is from 1 to  
 20, or

10



15 that the R group contains from 1 to 40 hydroxyl groups.  
 Examples of biologically active alpha-hydroxy acids  
 include, but are not limited to, citric acid and malic  
 acid. These polyanhydrides are prepared in the same  
 fashion as described for aromatic polyanhydrides.

20 Polyanhydrides used in the present invention can be  
 isolated by known methods commonly employed in the field of  
 synthetic polymers to produce a variety of useful products  
 with valuable physical and chemical properties. The new  
 polymers can be readily processed into pastes or solvent  
 25 cast to yield films, coatings, microspheres and fibers with  
 different geometric shapes for design of various medical  
 implants, and may also be processed by compression molding  
 and extrusion. Medical implant applications include the  
 use of aromatic polyanhydrides to form shaped articles such  
 30 as vascular grafts and stents, bone plates, sutures,  
 implantable sensors, implantable drug delivery devices,  
 stents for tissue regeneration, and other articles that  
 decompose harmlessly within a known time period.

Polyanhydrides of the present invention can also be  
 35 incorporated into oral formulations and into products such

-10-

as skin moisturizers, cleansers, pads, plasters, lotions, creams, gels, ointments, solutions, shampoos, tanning products and lipsticks for topical application.

The quantity of aromatic polyanhydride that  
5 hydrolyzes to form an amount of biologically active salicylate or alpha-hydroxy acid effective for the selected use can be readily determined by those of ordinary skill in the art without undue experimentation. The quantity essentially corresponds stoichiometrically to the amount of  
10 salicylate or alpha-hydroxy acid known to produce an effective treatment for the selected use.

The present invention relates to methods of using compositions comprising these polyanhydrides in any application wherein delivery of a salicylate or alpha-  
15 hydroxy acid is desired. For example, salicylates such as salicylic acid are used routinely to treat many skin disorders including, but not limited to, acne, dandruff, psoriasis, seborrheic dermatitis of the skin and scalp, calluses, corns, common warts and plantar warts. Salicylic  
20 acid is also topically applied as an antiseptic for wounds, ulcers, and skin abscesses as it is known to exert powerful static effects against Gram-negative and Gram-positive bacteria, yeasts, dermatophytes, molds and other microbes. These antifungal properties also render salicylic acid  
25 useful in the treatment of athlete's foot. Accordingly, topical application of a composition comprising an aromatic polyanhydride of the present invention which degrades to a biologically active salicylate is expected to be useful in the treatment of all of these conditions and/or injuries.

30 The anti-bacterial activity of salicylic acid also renders these polyanhydrides useful in agricultural applications. Solutions comprising a polyanhydride of Formula (I) can be applied topically to plants to establish microbial resistance against a wide range of pathogens.  
35 Salicylic acid treatment has also been shown to induce

-11-

thermotolerance in mustard seedlings. Accordingly, topical application of polyanhydrides of Formula (I) is also expected to induce thermotolerance in plants.

Salicylic acid has also been shown to have anti-  
5 cataract activity in patients suffering from galactosemic cataracts. Accordingly, a solution comprising an aromatic polyanhydride of Formula (I) can also be topically applied to the eye to inhibit cataract formation.

Salicylic acid is also a powerful anti-oxidant,  
10 neutralizing highly reactive, cell damaging molecules called free radicals. In fact, salicylic acid is often the standard by which the effectiveness of other anti-oxidants is measured. Anti-oxidants are administered orally and/or topically as antiviral agents. Anti-oxidants also inhibit  
15 UV-induced signal transduction and can be used as chemopreventative agents for skin cancer. In addition, the anti-oxidant properties of salicylates have been associated with anti-aging properties, protection against ischemia and reperfusion injury, and lowering of cholesterol levels and  
20 inhibition of clotting of blood. It is believed that compositions comprising an aromatic polyanhydride of Formula (I) will also exhibit these antioxidant properties. Thus, compositions comprising an aromatic polyanhydride of Formula (I) can also be used as antiviral agents,  
25 chemopreventative agents for skin cancer, anti-aging agents, and anti-clotting agents, and to provide protection against ischemia and reperfusion injury. Compositions of the present invention comprising a polyanhydride of Formula (III) which degrades to an alpha-hydroxy acid can be  
30 incorporated into various topical formulations and applied to the skin to promote smoother, clearer skin with less wrinkles. It is generally accepted that regular use of alpha-hydroxy acids improves the appearance of the skin by minimizing fine lines, softening dry, rough skin patches  
35 and fading age spots. Alpha-hydroxy acids are effective

-12-

exfoliators which dissolve the links that bind surface skin cells together causing dead cells to slough off. This process reveals the more youthful looking skin underneath which has more even skin tone, retains moisture and is less likely to form wrinkles. Topical application of a composition comprising a polyanhydride of Formula (III) provides an effective means for delivering alpha-hydroxy acids to the skin to promote smoother, clearer skin with less wrinkles.

10       The following non-limiting examples set forth hereinbelow illustrate certain aspects of the invention. All parts and percentages are by weight unless otherwise noted and all temperatures are in degrees Celsius. Except for acetic anhydride and ethyl ether (Fisher Scientific),  
15 all solvents and reagents were obtained from Aldrich Chemical. All solvents were HPLC grade. All other reagents were of analytical grade and were purified by distillation or recrystallization.

      All compounds were characterized by a proton nuclear  
20 magnetic resonance (NMR) spectroscopy, infrared (IR) spectroscopy, gel permeation chromatography (GPC), high performance liquid chromatography (HPLC), differential scanning calorimetry (DSC), and thermal gravimetric analysis (TGA). Infrared spectroscopy was performed on an  
25 ATI Mattson Genesis (M100) FTIR Spectrophotometer. Samples were prepared by solvent casting on NaCl plates. <sup>1</sup>H and <sup>13</sup>C NMR spectroscopy was obtained on a Varian 200 MHz or Varian 400 MHz spectrometer in solutions of CDCl<sub>3</sub> or DMSO-d<sub>6</sub> with solvent as the internal reference.

30       GPC was performed on a Perkin-Elmer Advanced LC Sample Processor (ISS 200) with PE Series 200 LC Pump and a PE Series LC Refractive Index Detector to determine molecular weight and polydispersity. The data analysis was carried out using Turbochrom 4 software on a DEC Celebris  
35 466 computer. Samples were dissolved in tetrahydrofuran

-13-

and eluted through a mixed bed column (PE PL gel, 5  $\mu$ m mixed bed) at a flow rate of 0.5 mL/minute. Samples (about 5 mg/mL) were dissolved into the tetrahydrofuran and filtered using 0.5  $\mu$ m PTFE syringe filters prior to column injection. Molecular weights were determined relative to narrow molecular weight polystyrene standards (Polysciences, Inc.).

Thermal analysis was performed on a Perkin-Elmer system consisting of a TGA 7 thermal gravimetric analyzer equipped with PE AD-4 autobalance and Pyris 1 DSC analyzer. Pyris software was used to carry out data analysis on a DEC Venturis 5100 computer. For DSC, an average sample weight of 5-10 mg was heated at 10°C/minute at a 30 psi flow of N<sub>2</sub>. For TGA, an average sample weight of 10 mg was heated at 20°C/minute under a 8 psi flow of N<sub>2</sub>. Sessile drop contact angle measurements were obtained with an NRL Goniometer (Rame-hart) using distilled water. Solutions of polymer in methylene chloride (10% wt/volume) were spun-coated onto glass slips, at 5,000 rpm for 30 seconds.

## 20 EXAMPLES

### Example 1: Preparation of 1,6-Bis(o-Carboxyphenoxy) Hexane Dicarboxylic Acid

To a mixture of salicylic acid (77.12 g, 0.5580 mole) and distilled water (84 mL) sodium hydroxide (44.71 g, 1.120 mole) was added. The reaction was brought to reflux temperature before 1,6-dibromohexane (45.21 g, 0.2790 mole) was added drop-wise. Reflux was continued for 23 hours after which additional sodium hydroxide (11.17 g, 0.2790 mole) was added. The mixture was refluxed for 16 more hours, cooled, filtered, and washed with methanol. The yield was 48.8%.

### Example 2: Preparation of 1,6-Bis(o-Carboxyphenoxy) Hexane Monomer (o-CPH)

The dicarboxylic acid of Example 1 was acetylated in

-14-

an excess of acidic anhydride at reflux temperature. The resulting monomer was precipitated with methylene chloride into an excess of diethyl ether. The yield was 66.8%.

**Example 3: Preparation of Poly(1,6-Bis(o-Carboxyphenoxy)**

**5 Hexane) (Poly(o-CPH))**

The monomer of Example 2 was polymerized in a melt condensation performed at 180°C for 3 hours under vacuum in a reaction vessel with a side arm. The polymerization vessel was flushed with nitrogen at frequent intervals.

10 The polymer was isolated by precipitation into diethyl ether from methylene chloride. The yield was quantitative.

All compounds were characterized by nuclear magnetic resonance spectroscopy, GPC, differential scanning calorimetry (DSC), thermal gravimetric analysis, contact  
15 angle measurements, UV spectroscopy, mass spectroscopy, elemental analysis and high pressure liquid chromatography (HPLC).

The o-CPH monomer was polymerized by melt polycondensation for 60 minutes at temperatures ranging  
20 from 100°C to 300°C. Analysis of the resulting polymers by GPC indicated that the highest molecular weight, coupled with the lowest polydispersity index occurred at 260°C.

The poly(o-CPH) was generally soluble in methylene chloride and chloroform, while the poly(p-CPH) was not. The  
25 poly(o-CPH) was slightly soluble in tetrahydrofuran, acetone and ethyl acetate.

Disks of poly(o-CPH), poly(p-CPH) and, as a reference, poly(lactic acid glycolic acid) were prepared and placed in 0.1 phosphate buffer solution at 37°C for 4  
30 weeks. The degradation media was replaced periodically. The degradation profile was linear up to three weeks time. In prior art polyanhydride systems, the aromatic groups are para-substituted. This substitution pattern results in higher melt and glass transition temperatures and decreased

-15-

solubility, thus ultimately making these parasubstituted polymers difficult to process.

Poly(o-CPH), unlike poly(p-CPH), has both a lower melting point (65°C vs. 143°C) and glass transition temperature (35°C vs. 47°C). It is also possible to solution cast poly(o-CPH) using low-boiling solvents whereas poly(p-CPH) is relatively insoluble in most organic and aqueous solvents. This structural modification gives a polymer whose hydrolysis products are chemically similar to aspirin. Aspirin is an anti-inflammatory agent derived from salicylic acid, which is one of the reagents used to synthesize the inventive polyanhydrides. Therefore, the degradation products of this polymer actually aid in patient recovery. Because of pliability and ease of processing, the aromatic polyanhydrides of the present invention have great potential as polymer scaffolds for wound healing.

**Example 4: Preparation of 1,3-bis(o-carboxyphenoxy)propane dicarboxylic acid**

1,3-dibromopropane (14.7 mL, 0.145 mole) was added to a mixture of salicylic acid (40.0 g, 0.290 mole), distilled water (44 mL) and sodium hydroxide (23.2 g, 0.580 mole) using the method described in Example 1. After 4 hours, additional sodium hydroxide (5.79 g, 0.145 mole) was added to the reaction mixture. Reflux was continued for another 4 hours, after which the mixture was cooled, filtered and washed using the methods described in Example 1. The yield was 37.7%

**Example 5: Preparation of poly(1,3-bis(o-carboxyphenoxy)propane)**

The dicarboxylic acid of Example 4 was acetylated using the methods of Example 2. The acetylated dicarboxylic acid was then polymerized using the methods described in Example 3. The resulting polymer had a  $M_w$  of 8,500 daltons and a polydispersity of 2.3.



-16-

Contact angle measurements on solvent-cast films demonstrated that the hexyl chain of the polymer of Example 3 increased the surface hydrophobicity relative to the shorter propyl chain of the polymer of Example 5. A comparison of thermal characteristics emphasized the effects of lengthening the alkyl chain. In particular, the polymer of Example 3 has a  $T_g$  of 34°C and a  $T_d$  of 410°C, while the polymer of Example 5 had a  $T_g$  of 50°C and a  $T_d$  of 344°C. Thus, the hexyl chain decreased the glass transition temperature ( $T_g$ ) relative to the propyl chain, reflecting the increased flexibility of the polymer chain. The opposite trend was observed for decomposition temperatures ( $T_d$ ), with the longer alkyl chain increasing the  $T_d$ .

Optimum polycondensation conditions were determined for the polymer of Example 3. Optimum conditions were defined as those that yielded a crude polymer with the highest molecular weight and highest  $T_g$ . Higher reaction temperatures decreased the  $M_w$  values (measured by GPC) with a concurrent increase in polydispersity. As expected for a condensation polymerization, longer reaction times yielded polymers with higher molecular weights. However, over longer reaction times, there appeared a subsequent decrease in  $T_g$ . Based on these results, the optimum conditions were defined as temperatures of 220°C for 150 minutes under a vacuum.

**Example 6: Preparation of 1,8-bis[o-(benzylcarboxy)carboxy phenyl] octane dicarboxylic acid ester**

The initial synthesis of poly(anhydride-ester) dicarboxylic acid monomers was attempted using the same methodology used for the poly(anhydride-ether) dicarboxylic monomers of Example 3. It was found, however, that the reactivity of the phenol was enhanced by benzylation of the carboxylic acid group. In addition, the solubility of benzyl salicylate in organic media increased the ability of the reaction to move forward.

-17-

Thus, benzyl salicylate (1.530 g, 6.720 mmole) and distilled tetrahydrofuran were combined under an inert atmosphere in a reaction flask. An ice-salt bath was placed under the reaction flask and the addition of 60% sodium hydride (0.4840 g, 12.10 mmole) followed. After one hour, sebacoyl chloride (0.7850 g, 3.280 mmole) was added drop-wise to the 0°C reaction mixture. After 30 minutes, the reaction mixture was vacuum filtered, the filtrate collected and the solvent removed to yield the free carboxylate as a white solid residue. Purification was performed using a chromatron with ethyl acetate/methylene chloride (20/80) as the solvent system. The yield was 43%.

**Example 7: Polymerization of Poly(1,8-bis(o-dicarboxyphenyl) octane)**

To remove the benzyl protecting groups, the 1,8-bis[(benzylcarboxy)carboxyphenyl]octane dicarboxylic acid ester of Example 6 (0.06000 g, 0.9620 mmole) was dissolved in methylene chloride in a reaction flask (60.00 mL). The catalyst Pd-C (10%, 1.200 g) was added to the reaction flask. After 30 minutes, the reaction was complete. The reaction mixture was filtered and the solvent removed to yield the free dicarboxylic acid as a white solid residue which was recrystallized using petroleum ether and methylene chloride. The yield was 45%.

The dicarboxylic acid was acetylated using the methods described in Example 2 and the acetylated dicarboxylic acid was then polymerized using the methods described in Example 3. The resulting polymer had a  $M_w$  of 3,000 daltons and a polydispersity of 1.40.

Subsequent polymerizations yielded polymers with  $M_w$ 's ranging from 2,000 to 5,000 daltons with corresponding polydispersities of approximately 1.40.

The poly(anhydride esters) of Example 7 were compression molded into circular discs and placed in phosphate buffered saline solution under acidic, neutral

-18-

and basic conditions. Over the course of a three-week degradation study, the polymers in the acidic and neutral solutions showed no observable changes, whereas the polymer in the basic media showed significant morphological changes over time.


**Example 8: Preparation of Poly[(1,8-bis(o-dicarboxyphenyl) octane)-(1,6-bis(p-carboxyphenoxy) hexane) copolymers**

The 1,8-bis(o-dicarboxyphenyl) octane of Example 2 was copolymerized with 1,6-bis(p-carboxyphenoxy) hexane using the methods described in Example 3. In an in vivo mouse study, each mouse was implanted with 2 polymers, the copolymer of Example 8 and poly(1,6-bis(p-carboxyphenoxy)hexane). Each polymer was compression molded for 1 to 5 minutes at 1 to 20 K psi depending on the thickness of polymer needed. The polymer was placed under the palatal gingival mucosa adjacent to the first maxillary molars.

-19-


What is Claimed is:

1. A composition comprising a polyanhydride which  
degrades to a biologically active salicylate or alpha-  
hydroxy acid, said polyanhydride comprising a repeating  
5 unit having the structure of Formula (I):



10

- wherein Ar is a substituted or unsubstituted aromatic ring  
and R is  $\text{---Z}_1\text{---R}_1\text{---Z}_1\text{---}$  substituted on each Ar ortho to the  
anhydride group, wherein  $\text{R}_1$  is a difunctional organic moiety  
and  $\text{Z}_1$  is a difunctional moiety selected from the group  
15 consisting of esters, amides, urethanes, carbamates and  
carbonates; or the structure of Formula (III):



20

- wherein R is an alkylene group containing from 1 to 20  
carbon atoms,  $\text{---(CH}_2\text{)}_x\text{---}$  wherein x is from 1 to 20, or

- 25  $\text{---}\overset{\text{Z}_2}{\underset{\text{Z}_1}{\text{CH}}}\text{---}$  wherein x is from 1 to 20 and  $\text{Z}_1$  and  $\text{Z}_2$  are OH so

that the R group contains from 1 to 40 hydroxyl groups.

- 30 2. A method of delivering a salicylate to a host  
comprising administering to a host a composition of claim 1  
wherein the polyanhydride comprises Formula (I).

3. The method of claim 2 wherein the composition is  
administered topically.

- 35 4. The method of claim 3 wherein the composition is

-20-

topically administered to the host to treat a skin disorder selected from the group consisting of acne, dandruff, psoriasis, seborrheic dermatitis of the skin and scalp, calluses, corns, common warts and plantar warts.

5           5. The method of claim 3 wherein the composition is topically administered to a host to prevent microbial infection.

6. The method of claim 5 wherein the host is an animal and the composition is topically applied as an  
10 antiseptic to a wound, ulcer or skin abscess.

7. The method of claim 5 wherein the host is a plant.

8. The method of claim 2 wherein the composition is administered to the host so that the salicylate can act as  
15 an anti-oxidant thereby neutralizing free radicals.

9. The method of claim 8 wherein the composition is administered to treat viral infections.

10. The method of claim 8 wherein the composition is administered to inhibit UV-induced signal transduction and  
20 development of skin cancer.

11. The method of claim 8 wherein the composition is administered to prevent blood clotting.

12. The method of claim 8 wherein the composition is administered to prevent tissue injury caused by ischemia  
25 and reperfusion.

13. The method of claim 2 wherein the composition is administered topically to the eye to inhibit cataract formation.

14. A method of delivering an alpha-hydroxy acid to  
30 a host comprising administering to a host a composition of claim 1 wherein the polyanhydride comprises Formula (III).

15. The method of claim 14 wherein the composition is administered topically to promote smoother, clearer skin with less wrinkles.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
26 April 2001 (26.04.2001)

PCT

(10) International Publication Number  
**WO 01/28492 A3**

(51) International Patent Classification<sup>7</sup>: **A61K 31/74**

(21) International Application Number: **PCT/US00/27962**

(22) International Filing Date: 11 October 2000 (11.10.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/422,294 21 October 1999 (21.10.1999) US

(71) Applicant: **RUTGERS, THE STATE UNIVERSITY**  
[US/US]; Old Queens Building, Somerset and George  
Streets, New Brunswick, NJ 08901 (US).

(72) Inventor: **UHRICH, Kathryn, E.**; 920 Bloomfield Street,  
#1, Hoboken, NJ 07030 (US).

(74) Agent: **VISKININS, Ann, S.**; Schwegman, Lundberg,  
Woessner & Kluth, P.O. Box 2938, Minneapolis, MN  
55402 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:  
13 September 2001

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



**WO 01/28492 A3**

(54) Title: **POLYANHYDRIDES WITH BIOLOGICALLY ACTIVE DEGRADATION PRODUCTS**

(57) Abstract: Polyanhydrides which degrade into biologically active salicylates and alpha-hydroxy acids and methods of using these polyanhydrides to deliver the salicylates and alphahydroxy acids to a host are provided.

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US00/27962

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A 61 K 31/74  
US CL : 424/78.04 514/772.3  
According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
U.S. : 424/78.04 514/772.3

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,264,540 A (COOPER ET AL.) 23 November 1993, see example.	1-15
Y		

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G* document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

US 5,902,599 A (ANSETH ET AL.) 11 May 1999, see example 3.

Date of mailing of the international search report

02 FEBRUARY 2001 12 APR 2001

Names and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231  
Facsimile No.

Authorized officer

ISA/US

Telephone No. (703) 305-3014

**THIS PAGE BLANK (USPTO)**